Amendments to the Claims

1-9. (Cancelled)

10. (Currently Amended) An absorbent article comprising a liquid-permeable topsheet, a liquid-impermeable backsheet, and a liquid retentive absorbent member interposed between the topsheet and the backsheet, wherein

said backsheet comprises a laminated sheet composed of a breathable film printed with a multicolor pattern, ~~and~~ a <u>first</u> nonwoven material <u>and a second nonwoven material laminated on said</u> <u>first nonwoven material</u>, the <u>first</u> nonwoven material being superposed on the printed side of said film,

<u>an elastic member is fixedly disposed between said first and</u> <u>second nonwoven materials,</u>

<u>a total basis weight which is a sum of a basis weight of said</u> <u>first nonwoven material and a basis weight of said second nonwoven</u> <u>material is 20 to 50g/m^2, and a total thickness which is a sum of a</u> <u>thickness of said first nonwoven material and a thickness of said</u> <u>second nonwoven material before laminating said first and second</u> <u>nonwoven materials is 0.5 to 3.0 mm,</u>

the printed area of said film has an L* value of 10 to 93 and a C* value of 20 to 120 as measured with a color difference meter,

2

~~said nonwoven material has a light transmittance of 40 to 83%~~

~~and a basis weight of 30 to 45 g/m²~~

<u>a total light transmittance of said first nonwoven material</u>

<u>and said second nonwoven material is 40 to 83%;</u> and

nonprinted background areas on the printed side of said

breathable film have a b* value of 0 to -5.

11. (Previously Presented) The absorbent article according to

claim 10, wherein said b* value is less than 0 and greater than or

equal to -5.

12. (**NEW**) The absorbent article according to claim 10, wherein

50% or more of the total area of the printed area on the breathable

film satisfies the requirement of an L* value of 10 to 93 and a C*

value of 20 to 120 as measured with a color difference meter.

13. (**NEW**) The absorbent article according to claim 10, wherein

the moisture vapor transport rate of the breathable film is 0.5 to

4.0 g/(100 cm²·hr) measured in accordance with JIS Z0208.